



NEGIN ZEREH Co.

Industrial, Marine, Water Base, Architectural Paint

ELASTIC ACRYLIC TOPCOAT NZ-133

| Product Description

NZ-133 is a physically drying topcoat based on elastic acrylic emulsion resin.

| Recommended Use

As a topcoat for interior and exterior of building and a topcoat on isolated surfaces.

| Outstanding Characteristics

- High adhesion to different metallic surfaces
- High gloss and color retention
- Good flexibility
- Good appearance
- Good UV resistance
- Good weather resistance

| Surface Preparation

The surface must be clean, dry and free from salt and any other contaminants such as dust, grease, oil and loose paint.

| Technical Data

Finish	Semi-gloss, Gloss
Color	Upon Request
Solid by volume	45±3%
Specific Gravity	1.25±0.10 gr/cm ³
Recommended D.F.T.	50-70 microns
Theoretical coverage	7.1-5.2 m ² /kg
	Practical coverage depends on loss factor
Touch dry	25 min. at 20°C
Hard dry	4 hrs. at 20°C
Shelf life	12 months at 25°C
Package	20 liter container

| Application Details

Application method	Air spray, Brush ,Roller
Surface temperature	10-45 °C
Mixing ratio	Single Pack
Thinner/cleaner	Water
Pot Life	N/A
Recoat interval	Min 4 hrs. at 20°C
	Max indefinite
	Recoating intervals related to later conditions of exposure

Note: Film thickness may be specified in another film thickness than indicated depending on purpose and area of use. This will alter the spreading rate and may influence the amount of thinning necessary, drying time and recoating interval.

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Neginzereh-pars Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Neginzereh-pars representative to obtain the most recent Product Data Information and Application Bulletin. The Neginzereh-pars Company warrants our products to be free of manufacturing defects in accord with applicable Neginzereh-pars quality control procedures.