



ALKYD IRON OXIDE RED LEAD PRIMER NZ-202

Product Description

NZ-202 is a primer based on raw linseed oil and long oil alkyd resin, containing red lead and Iron oxide pigments, according to IPS-M-TP-115.

Recommended Use

For use on interior and exterior of structural steel to be topcoat with conventional paint systems, preferably as a maintenance primer for protection of steel in mild to medium atmospheric corrosive environments.

Outstanding Characteristics

- Rust preventing
- Excellent Recoat ability
- Not suitable for immersion
- High resistance in mildly to moderately corrosive environment

Surface Preparation

For new steel abrasive blasting to minimum Sa2, alternatively power tool cleaning to SSPC SP3. For maintenance remove oil and grease and any other contaminants by suitable detergent and consequently by high-pressure fresh water cleaning. Remove all rust and loose material by abrasive blasting or power-tool cleaning, and remove any dusts and residues before painting.

Technical Data

Finish	Matt
Color	Red-orange
Solid by volume	50±3%
Specific Gravity	1.50±0.10 gr/cm ³
Flash point	38 °C
Recommended D.F.T.	40-60 microns
Theoretical coverage	8.3-5.6 m ² /kg Practical coverage depends on loss factor
Touch dry	5-7 hrs. at 20 °C
Fully cured	7days at 20 °C
Thermal resistance	Max. 100 °C (dry exposure)
Shelf life	12 months at 25 °C
Package	20 liter container

Application Details

Application method	Air/Airless spray, Brush ,Roller
Surface temperature	10-45 °C
Mixing ratio	Single Pack
Thinner/cleaner	NZT-200
Pot Life	N/A
Recoat interval	Min 24 hrs. at 20 °C Max 30 days at 20 °C Recoating intervals related to later conditions of exposure
Nozzle orifice	0.019"-0.021"
Nozzle pressure	150 bar/2175 psi Airless spray is indicative and subject to adjustment
Application condition	Apply only on a dry and clean surface with a temperature 3 °C above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

Note: Film thickness may be specified in another film thickness than indicated depending on purpose and area of use. This will alter the spreading rate and may influence the amount of thinning necessary, drying time and recoating interval.

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Neginzereh-pars Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Neginzereh-pars representative to obtain the most recent Product Data Information and Application Bulletin. The Neginzereh-pars Company warrants our products to be free of manufacturing defects in accord with applicable Neginzereh-pars quality control procedures.