



**NEGIN ZEREH Co.**

Industrial, Marine, Water Base, Architectural Paint

## **EPOXY ESTER SEALER NZ-554**

### **Product Description**

**NZ-554** is a single pack sealer based on air drying epoxy ester resin.

### **Recommended Use**

As a sealer in industrial and marine concrete structures such as refineries, petrochemical plants, bridges, tanks and water sewage plants.

### **Outstanding Characteristics**

- Excellent penetration
- Good adhesion to previous and subsequent coats
- Toughness and durability of film
- Good temperature resistance

### **Surface Preparation**

The surface must be clean and dry. Any contamination such as dirt, grease, oil, salt and any other foreign materials should be removed.

### **Technical Data**

<b>Finish</b>	Semi-flat, Semi-gloss
<b>Color</b>	Color less
<b>Solid by volume</b>	36±3%
<b>Specific Gravity</b>	1.10±0.05 gr/cm <sup>3</sup>
<b>Flash point</b>	23 °C
<b>Recommended D.F.T.</b>	20-40 microns
<b>Theoretical coverage</b>	17.0-7.9 m <sup>2</sup> /kg Practical coverage depends on loss factor
<b>Touch dry</b>	30 min. at 20 °C
<b>Hard dry</b>	48 hrs. at 20 °C
<b>Thermal resistance</b>	Max. 140 °C (dry exposure)
<b>Shelf life</b>	12 months at 25 °C
<b>Package</b>	20 liter containers

### **Application Details**

<b>Application method</b>	Air/Airless spray, Brush, Roller
<b>Surface temperature</b>	10-45 °C
<b>Mixing ratio</b>	Single Pack
<b>Thinner/cleaner</b>	NZT-500/2
<b>Pot Life</b>	N/A
<b>Recoat interval</b>	Min 24 hrs. at 20 °C Max 3 months at 20 °C Recoating intervals related to later conditions of exposure
<b>Nozzle orifice</b>	0.019"-0.021"
<b>Nozzle pressure</b>	150 bar/2175 psi Airless spray is indicative and subject to adjustment
<b>Application condition</b>	Apply only on a dry and clean surface with a temperature 3 °C above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

**Note:** Film thickness may be specified in another film thickness than indicated depending on purpose and area of use. This will alter the spreading rate and may influence the amount of thinning necessary, drying time and recoating interval.

**Safety:** Handle with care. Before and during use, observe all safety labels on packaging and paint containers. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Neginzereh-pars Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Neginzereh-pars representative to obtain the most recent Product Data Information and Application Bulletin. The Neginzereh-pars Company warrants our products to be free of manufacturing defects in accord with applicable Neginzereh-pars quality control procedures.