



NEGIN ZEREH Co.

Industrial, Marine, Water Base, Architectural Paint

ALKYD MARINE TOPCOAT NZ-206-M

Product Description

NZ-206-M is a versatile finish coat based on alkyd enamel which forms a weather resistant coating .it is flexible and resistant to saltwater and spillage of mineral oil and other aliphatic hydrocarbons.

Recommended Use

As a general purpose finishing coat in alkyd system on exterior and interior steel and woodwork in mildly to moderately corrosive environment. Recommended for engines, topside, deck and superstructure.

Outstanding Characteristics

- Good gloss and color retention
- Excellent spray ability
- Excellent flexibility
- Good resistance in mildly to moderately corrosive environments

Surface Preparation

The surface must be clean, dry and free from any contamination such as grease, rust, salt and loose paint, chalk and other foreign matter than could interfere with adhesion.

Technical Data

Finish	Gloss
Color	Upon Request
Solid by volume	50±3%
Specific Gravity	1.20±0.10 gr/cm ³
Flash point	38 °c
Recommended D.F.T.	40-60 microns
Theoretical coverage	13.2-7.8 m ² /lit Practical coverage depends on loss factor
Touch dry	5 hrs. at 20° c
hard dry	16 hrs. at 20° c
Thermal resistance	Max. 100° c (dry exposure)
Shelf life	12 months at 25° c
Package	20 liter container

Application Details

Application method	Air/Airless spray, Brush ,Roller
Surface temperature	10-50 ° c
Mixing ratio	Single pack
Thinner/cleaner	NZT-200-M
Pot Life	N/A
Recoat interval	Min 16 hrs. at 20° c Max 30 days at 20° c Recoating intervals related to later conditions of exposure
Nozzle orifice	0.019"-0.021"
Nozzle pressure	150 bar/2175 psi Airless spray is indicative and subject to adjustment
Application condition	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

Note: Film thickness may be specified in another film thickness than indicated depending on purpose and area of use. This will alter the spreading rate and may influence the amount of thinning necessary, drying time and recoating interval.

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Neginzereh-pars Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Neginzereh-pars representative to obtain the most recent Product Data Information and Application Bulletin. The Neginzereh-pars Company warrants our products to be free of manufacturing defects in accord with applicable Neginzereh-pars quality control procedures.

Ver.01,2025