



**NEGIN ZEREH Co.**

Industrial, Marine, Water Base, Architectural Paint

# **POLYAMINE CURED EPOXY PHENOLIC INTERMEDIATE NZ-571-M**

## **| Product Description**

**NZ-571-M** is a two component, high performance polyamine cured, phenolic epoxy (Novella) paint, which cures to a coating with excellent resistance to a wide range of chemicals.

## **| Recommended Use**

As a protective coating in tank lining or steel structures to be immersed or exposed to splash or spillage of sea or potable water, solvents & chemicals.

## **| Outstanding Characteristics**

- Excellent oil resistance
- Excellent chemical resistance against weak acids, alkalis & solvents
- Corrosion resistance in moderately to severely environment
- Suitable for immersion in warm water

## **| Surface Preparation**

Surface should be cleaned from oil, grease, dust, salt and any other foreign materials.

## **| Technical Data**

<b>Finish</b>	Flat, semi-flat After exposure to heat the gloss is reduced
<b>Color</b>	White, gray After exposure to heat the color is changed
<b>Solid by volume</b>	60±3%
<b>Specific Gravity</b>	1.40±0.1 gr/cm <sup>3</sup>
<b>Flash point</b>	30 °C
<b>Recommended D.F.T.</b>	100-150 microns
<b>Theoretical coverage</b>	6.3-3.8 m <sup>2</sup> /lit Practical coverage depends on loss factor
<b>Touch dry</b>	2 hrs. at 20 °C
<b>Fully cured</b>	7 days at 20 °C
<b>Thermal resistance</b>	Max. 180 °C (dry exposure)
<b>Shelf life</b>	12 months at 25 °C
<b>Package</b>	20 & 4 liter containers

## **| Application Details**

<b>Application method</b>	Air/Airless spray, Brush, Roller
<b>Surface temperature</b>	10-50 °C
<b>Mixing ratio</b>	Refer to the can label
<b>Thinner/cleaner</b>	NZT-500/6-M
<b>Pot Life</b>	2 hrs. at 20 °C
<b>Recoat interval</b>	Min 24 hrs. at 20 °C Max 3 days at 20 °C Recoating intervals related to later conditions of exposure
<b>Nozzle orifice</b>	0.017"-0.021"
<b>Nozzle pressure</b>	200 bar/2900 psi Airless spray is indicative and subject to adjustment
<b>Application condition</b>	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

**Note:** Film thickness may be specified in another film thickness than indicated depending on purpose and area of use. This will alter the spreading rate and may influence the amount of thinning necessary, drying time and recoating interval.

**Safety:** Handle with care. Before and during use, observe all safety labels on packaging and paint containers. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Neginzereh-pars Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Neginzereh-pars representative to obtain the most recent Product Data Information and Application Bulletin. The Neginzereh-pars Company warrants our products to be free of manufacturing defects in accord with applicable Neginzereh-pars quality control procedures.

Ver.01,2025